



# TUSCAN CARRARA

Elevate your interiors with the timeless beauty of the Tuscan Carrara Series - an embodiment of timeless elegance and classic beauty.

Crafted from rectified glazed porcelain, these tiles capture the essence of Carrara marble with exquisite detail and superior craftsmanship.

**Available in:**

- 30x30 Matt floor/wall
- 30x60 Matt & Polished floor/wall
- 60x60 Matt & Polished floor/wall
- 120x60 Matt & Polished floor/wall

**Features:**

- Varying faces with different veining throughout to create a luxe & authentic marble look giving depth and character to any space.

Whether you prefer the understated allure of Matt finish or luxurious shine of Polished surfaces, Tuscan Carrara brings a touch of sophistication to any room.

## Packing Information

Tile description		Quantity per Box		
Size (cm)	Texture	Pieces	Sqm	Weight
30x30	Matt	11	0.99	19.80
30x60	Matt & Polish	8	1.44	26.10
60x60	Matt & Polish	4	1.44	28.50
60x120	Matt & Polish	2	1.44	37.00



120 X 60



60 X 60










30 X 60










30 X 30

# Technical Specifications: Tuscan Matt

	Properties	Test Method		Required Value		Value
	Water absorption	<b>MS ISO 10545-3:2001</b>		$0.5\% < E_v \leq 3\%$  Individual maximum 3.3%		<b>2.3%</b>  <b>2.0%~2.5%</b>
	Determination of dimensions	<b>Length and width</b> The deviation, of the average size for each tile from the work size	MS ISO 10545-2:2002	$N \geq 15\text{cm}$	$\pm 0.3\%$ $\pm 1.0\text{mm}$	$0 \sim +0.02\%$ $0 \sim +0.2\text{mm}$
		<b>Thickness</b> The deviation of the average thickness of each tile from the work size thickness	MS ISO 10545-2:2002	$N \geq 15\text{cm}$	$\pm 5\%$ $\pm 0.5\text{mm}$	$-0.2\% \sim +1.4\%$ $0 \sim +0.1\text{mm}$
		<b>Straightness of sides</b> The maximum deviation from straightness related to the corresponding work sizes	MS ISO 10545-2:2002	$N \geq 15\text{cm}$	$\pm 0.3\%$ $\pm 0.8\text{mm}$	$0 \sim +0.02\%$ $0 \sim +0.1\text{mm}$
		<b>Rectangularity</b> The maximum deviation from the Rectangularity related to the corresponding work sizes	MS ISO 10545-2:2002	$N \geq 15\text{cm}$	$\pm 0.3\%$ $\pm 1.5\text{mm}$	$+0.04\% \sim +0.06\%$ $+0.2\text{mm} \sim +0.4\text{mm}$
	Breakage strength	<b>MS ISO 10545-4:2003</b>		$\geq 1100$		<b>1353</b>
	Modulus of rupture	<b>MS ISO 10545-4:2003</b>		Minimum 30  Individual minimum 27		<b>30.8</b>  <b>29.6~31.8</b>
	Chemical resistance	a) Household chemicals: Ammonium chloride, 100g/L	MS ISO 10545-13:2018	Minimum B	A	
		b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	MS ISO 10545-13:2018	Minimum B	A	
	Stain resistance	a) Green staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		b) Red staining agent in light oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		c) Iodine, 13g/L solution in alcohol	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
		d) Olive oil	MS ISO 10545-14:2018	Minimum Class 3	Class 5	
	Origin	MADE IN CHINA				

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.

# Technical Specifications: Tuscan Polish

	Properties	Test Method		Required Value	Value
	Water absorption	EN ISO 10545-3:2018		$E_b \leq 0.5\%$ 单个值不大于 0.6% Individual maximum 0.6%	0.05% 0.04% ~ 0.06%
	Determination of dimensions	长度和宽度 Length and Width 每块砖的平均尺寸相对于工作尺寸的允许偏差 The permissible deviation of the average size for each tile (4 sides) from the work size	EN ISO 10545-2:2018	$\pm 0.6\%$	-0.06%~-0.03%
		厚度 Thickness 每块砖厚度的平均值相对于工作尺寸的最大允许偏差 The permissible deviation, of the average thickness of each tile from the work size thickness	EN ISO 10545-2:2018	$\pm 2.0\text{mm}$	-0.3mm ~-0.2mm
				$\pm 5\%$	-0.6%~+0.6%
				$\pm 0.5\text{mm}$	-0.1mm ~ +0.1mm
	Breakage strength	EN ISO 10545-4:2019		$\geq 1300$	2418
	Modulus of rupture	EN ISO 10545-4:2019		平均值 $\geq 35$ Minimum 35 单个值 $\geq 32$ Individual minimum 32	48.8 47.0~50.4
	Chemical resistance	家庭化学试剂: 氯化铵溶液, 100g/L a) Household chemicals: Ammonium chloride, 100g/L	EN ISO 10545-13:2016	不低于 B 级 Minimum class B	A
		b) 游泳池盐类: 次氯酸钠溶液, 20mg/L b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	EN ISO 10545-13:2016	不低于 B 级 Minimum class B	A
	Stain resistance	a) 轻油中的铬绿 a) Green staining agent in light oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		b) 轻油中的红色污染物 b) Red staining agent in light oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		c) 13g/L 碘酒液 c) Iodine, 13g/L solution in alcohol	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
		d) 橄榄油 d) Olive oil	EN ISO 10545-14:2015	不低于 3 级 Minimum Class 3	5 级 Class 5
	Origin	MADE IN CHINA			

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.