

















Technical Specifications: AURA

| | Properties | Test Method | Required Value | Value |
|-----|-----------------------------------|------------------|--|---------------------|
| | Water absorption | ASTM C373-18 | 7.0% <wa≤20.0%< td=""><td>15.9% ~ 16.7%</td></wa≤20.0%<> | 15.9% ~ 16.7% |
| | Crazing Resistance | ASTM C424-93 | Pass | Fully resistance |
| Т | Breakage strength | ASTM C648-04 | Average ≥ 0.55 | 0.86 |
| A A | | | Individual ≥ 0.44 | 0.82~0.93 |
| | Scratch Hardness of Surface | EN 15771:200 | | 5 |
| J | Chemical resistance | ASTM C650-04 | | Class A |
| 523 | Stain resistance | ASTM C1378-04 | | Class A |
| | Origin | VIETNAM | | |

Please note that this technical specification sheet is issued to you on an INDICATION ONLY basis as information is subject to shade/production variations, not necessarily to material you would be receiving. No responsibility will be held for the item not meeting this result. It is the responsibility of the end user to carry out appropriate testing for the tiles intended use.

Packing Information

| Tile | e description | Quantity per Box | | |
|-----------|---------------|------------------|------|--------------|
| Size (cm) | Texture | Pieces | Sqm | Weight (kgs) |
| 7.5x30 | Gloss | 44 | 0.99 | 13.20 |

